

# 2348NC

Polypropylene Impact Copolymer / Injection Molding

## PRODUCT DESCRIPTION

2348NC is a Polypropylene Impact Copolymer with the characteristic of medium melt flow for using in injection molding process. It contains UV stabilizer and anti-static agent.

### TYPICAL APPLICATION

- Injection Molding parts
- Automotive parts
- Appliances parts

### PRODUCT FEATURES

- UV Resistance
- Anti-static performance
- Good balance between impact and stiffness

### COMPLIANCE

- FDA US 21 CFR 177.1520
- RoHS
- REACH

PHYSICAL PROPERTIES	TEST METHOD	UNIT	VALUE
Melt Flow Index (2.16 kg/230 °C)	ASTM D1238	g/10 min	11
Density	ASTM D792	g/cm <sup>3</sup>	0.90
Tensile Strength at Yield	ASTM D638	MPa	27
Elongation at Yield	ASTM D638	%	6
Izod Notched Impact Strength (at -20 °C)	ASTM D256	J/m	47
Flexural Modulus (1% SECANT)	ASTM D790	MPa	1300
Rockwell Hardness	ASTM D785	R-Scale	92
Heat Distortion Temperature (0.45 MPa)	ASTM D648	°C	105

Remark: The values presented on the above are typical laboratory, not to be construed as specifications and may vary within moderate ranges. The applicability or the accuracy of this information or the suitability of our products cannot be guaranteed because the conditions of use on the part or our uses are beyond our control.

# 2348NC

Polypropylene Impact Copolymer / Injection Molding

## PROCESSING TECHNIQUE

Cylinder Temperature: 190 - 240 °C  
Mold Temperature : 40 - 60 °C  
Injection Pressure : 30 - 80% of maximum pressure  
Holding Pressure : Relative to injection pressure  
Back Pressure : 0 - 20 of maximum pressure  
Injection Speed : Low to medium of maximum speed

\*However, the actual processing conditions depend on mold design, power of machine, equipment and other environments.

## PRODUCT PACKAGING

- 25 kg loose bag

## STORAGE

Storage in 20 - 80% relative humidity at ambient temperature preferably not higher than 38 °C (100 °F).

Dry environment with the exclusion of contamination.

Protection against direct sunlight, radiation and artificial light containing UV-Radiation.

Protection from ozone-generating electrical devices.

Under these optimal conditions, the physical properties of resins should remain stable with the exception of the yellowness index which is expected to increase over time.

More information provide in safety data sheet.

## SAFETY

This product is not classified as hazardous material for more information please refer to safety data sheet.

## RECYCLING

It is an undisputed fact that the product can be recycled or disposed of without any problem.