

1140U

Polypropylene Homopolymer / Thin-wall Transparency Injection Molding

PRODUCT DESCRIPTION

1140U is a Polypropylene Homopolymer with the characteristic of high flow for production of long path and thin wall injection molding process.

TYPICAL APPLICATION

- Thin wall packaging
- Long path food container
- Complex parts

PRODUCT FEATURES

- High Flow ability
- High Speed injection molding
- High Transparency thin-wall
- Dimensional stability

COMPLIANCE

- FDA US 21 CFR 177.1520
- Commission Regulation (EU) No. 10/2011
- RoHS
- REACH

| PHYSICAL PROPERTIES | TEST METHOD | UNIT | VALUE |
|---|-------------|-------------------|-------|
| Melt Flow Index (2.16 kg/230 °C) | ASTM D1238 | g/10 min | 60 |
| Density | ASTM D792 | g/cm ³ | 0.9 |
| Tensile Strength at Yield | ASTM D638 | MPa | 39 |
| Elongation at Yield | ASTM D638 | % | 9 |
| Izod Notched Impact Strength (at 23 °C) | ASTM D256 | J/m | 27 |
| Flexural Modulus (1% SECANT) | ASTM D790 | MPa | 1750 |
| Rockwell Hardness | ASTM D785 | R-Scale | 109 |
| Heat Distortion Temperature (0.45 MPa) | ASTM D648 | °C | 120 |
| Haze (1 mm) | ASTM D1003 | % | 40 |

Remark: The values presented on the above are typical laboratory, not to be construed as specifications and may vary within moderate ranges. The applicability or the accuracy of this information or the suitability of our products cannot be guaranteed because the conditions of use on the part or our uses are beyond our control.

1140U

Polypropylene Homopolymer / Thin-wall Transparency Injection Molding

PROCESSING TECHNIQUE

Cylinder Temperature: 190 - 240 °C
Mold Temperature : 40 - 60 °C
Injection Pressure : 30 - 80% of maximum pressure
Holding Pressure : Relative to injection pressure
Back Pressure : 0 - 20 of maximum pressure
Injection Speed : Low to medium of maximum speed

*However, the actual processing conditions depend on mold design, power of machine, equipment and other environments.

PRODUCT PACKAGING

- 25 kg loose bag
- 25 kg stretch wrap on palletized
- 750 kg jumbo bag

For further information, contact the IRPC's Sales representative.

STORAGE

Storage at ambient temperature preferably not higher than 38 °C (100 °F).

- Dry environment with the exclusion of contamination.
- Protection against direct sunlight, radiation and artificial light containing UV-Radiation.
- Protection from ozone-generating electrical devices.
- Under these optimal conditions, the physical properties of resins should remain stable with the exception of the yellowness index which is expected to increase over time.

More information provide in safety data sheet.

SAFETY

This product is not classified as hazardous material for more information please refer to safety data sheet.

RECYCLING

It is an undisputed fact that the product can be recycled or disposed of without any problem.