

# 3340HMD

Polypropylene Random Copolymer/Medical Extrusion Blow Molding

## PRODUCT DESCRIPTION

3340HMD is a Medical Grade Polypropylene Random Copolymer with the characteristic of high clarity and high impact for using extrusion blow molding process.

### TYPICAL APPLICATION

- IV bottle
- Saline bottle
- Medical bottle

### PRODUCT FEATURES

- Medical grade
- High impact resistance
- High clarity and high gloss
- Without optical brightener
- Odorless
- Ethylene oxide/Autoclave sterilization

### COMPLIANCE

- FDA US 21 CFR 177.1520
- Commission Regulation (EU) No. 10/2011
- RoHS
- REACH
- USP Class VI
- EP 3.1.6

PHYSICAL PROPERTIES	TEST METHOD	UNIT	VALUE
Melt Flow Index (2.16 kg/230 °C)	ASTM D1238	g/10 min	2
Density	ASTM D792	g/cm <sup>3</sup>	0.90
Tensile Strength at Yield	ASTM D638	MPa	27
Elongation at Yield	ASTM D638	%	13
Izod Notched Impact Strength (at 23 °C)	ASTM D256	J/m	250
Flexural Modulus (1% SECANT)	ASTM D790	MPa	850
Rockwell Hardness	ASTM D785	R-Scale	84
Heat Distortion Temperature (0.45 MPa)	ASTM D648	°C	83
Haze (1 mm)	ASTM D1003	%	8

Remark: The values presented on the above are typical laboratory, not to be construed as specifications and may vary within moderate ranges. The applicability or the accuracy of this information or the suitability of our products cannot be guaranteed because the conditions of use on the part or our uses are beyond our control.

# 3340HMD

Polypropylene Random Copolymer/Medical Extrusion Blow Molding

## PROCESSING TECHNIQUE

Cylinder Temperature : 180 - 200 °C  
Die Temperature : 190 - 200 °C  
Cooling Water Temperature : 20 - 25 °C  
Air Pressure : 6 - 7 Bar

\*However, the actual processing conditions depend on mold design, power of machine, equipment and other environments.

## PRODUCT PACKAGING

- 25 kg loose bag

## STORAGE

Storage in 20 - 80% relative humidity at ambient temperature preferably not higher than 38 °C (100 °F).

Dry environment with the exclusion of contamination.

Protection against direct sunlight, radiation and artificial light containing UV-Radiation.

Protection from ozone-generating electrical devices.

Under these optimal conditions, the physical properties of resins should remain stable with the exception of the yellowness index which is expected to increase over time.

More information provide in safety data sheet.

## SAFETY

This product is not classified as hazardous material for more information please refer to safety data sheet.